



Catálogo de Productos

Merluza Clase 6x36


- Alma de Acero
- Galvanizado
- 6x31WS
- 6x36WS
- 6x41WS
- 6x43SWS
- 6x49SWS




6x31WS




6x36WS



6x41WS



6x43SWS



6x49SWS

Tabla de Resistencias a la tensión y Pesos (pulgadas)

Diámetro (pulgadas)	Peso Aproximado (lb/ft)	Resistencia a la Ruptura (lbs.)	
		Arado Mejorado	Arado Extramejorado
1/4	0.12	5,890	6,790
5/16	0.18	9,150	10,540
3/8	0.26	13,120	15,100
7/16	0.35	17,780	20,380
1/2	0.46	23,000	26,600
9/16	0.59	29,000	33,600
5/8	0.72	35,800	41,200
3/4	1.04	51,200	58,800
7/8	1.42	69,200	79,600
1	1.85	89,800	103,400
1 1/8	2.34	113,000	130,000
1 1/4	2.89	138,800	159,800
1 3/8	3.50	167,000	192,000
1 1/2	4.16	197,800	228,000
1 5/8	4.88	230,000	264,000
1 3/4	5.67	266,000	306,000
1 7/8	6.50	304,000	348,000
2	7.39	344,000	396,000
2 1/8	8.35	384,000	442,000
2 1/4	9.36	430,000	494,000
2 3/8	10.40	478,000	548,000
2 1/2	11.60	524,000	604,000
2 5/8	12.80	576,000	658,000
2 3/4	14.00	628,000	736,000
2 7/8	15.30	682,000	796,000
3	16.60	740,000	856,000
3 1/8	18.00	798,000	920,000

3 1/4	19.50	858,000	984,000
3 3/8	21.00	918,000	1,074,000
3 1/2	22.70	982,000	1,144,000
3 3/4	26.00	1,114,000	1,290,000
4	29.60	1,254,000	1,466,000
Normas de Referencia: ASTM-A-1023; API 9A			

Tabla de Resistencias a la tension y Pesos (milímetros)

Diámetro (mm)	Peso Aproximado (kg/m)	Resistencia a la Ruptura (Toneladas Metricas)	
		Arado Mejorado	Arado Extramejorado
6.35	0.18	2.7	3.1
7.94	0.27	4.1	4.8
9.53	0.39	6.0	6.9
11.1	0.52	8.1	9.2
13	0.68	10.4	12.1
14.5	0.88	13.2	15.2
16	1.07	16.2	18.7
19	1.55	23.2	26.7
22	2.11	31.4	36.1
26	2.75	40.7	46.9
29	3.48	51.3	59.0
32	4.30	63.0	72.5
35	5.21	75.7	87.1
38	6.19	89.7	103.0
42	7.26	104.0	120.0
45	8.44	121.0	139.0
48	9.67	138.0	158.0
52	11.0	156.0	180.0
54	12.40	174.0	200.0
58	13.90	195.0	224.0
60	15.50	217.0	249.0
64	17.30	238.0	274.0
67	19.00	261.0	299.0
71	20.80	285.0	333.0
74	22.80	309.0	361.0
77	24.70	336.0	389.0
80	26.80	362.0	417.0
83	29.00	389.0	447.0
87	31.30	416.0	487.0
90	33.80	445.0	519.0
96	38.70	505.0	585.0
103	44.00	569.0	665.0
Normas de Referencia: ASTM-A-1023; API 9A			